



正 本
ORIGINAL

試驗報告

日期: Feb. 14, 2014 收件日期: Feb. 10, 2014 TEST REPORT

報告編號: TFF3B034-IPC 報告頁次/頁數: (P1/1) 來文字號: NIL
Report No.: TFF3B034-IPC Quantity: Page Order/Pages: Ref. No.:

報告抬頭: VOLL WILL ENTERPRISE CO., LTD. (T2401) 試件類別: Knitted Fabric
Report Title: Item:


地址: NO. 186, SEC. 3, CHIEN KANG RD., 708 TAINAN, TAIWAN, R.O.C.
Address:

Test Items	Test Results	Test Methods
Antistatic Test-Surface Resistivity(Ω /Square)	4.3E+11	AATCC 76-2011 Temperature: 20 °C Humidity: 40 % RH

Note: 2.0E+02 is equal to 200, 1.3E+04 is equal to 13000, etc.

Note: Sample description is given by the client: FIR-SKIN GX

FAR INFRARED RAYS



附記: 1. 本報告僅對樣品負責, 樣品保留期限為一個月。
Note: This report is only responsible for the submitted sample(s), which will be kept for one month period.
2. 本報告非經本檢測及驗證部書面同意, 不得摘錄複製, 但全部複製除外。
This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
3. 試驗報告所載事項不得作為公開廣告及商業推銷之用。
The test report should not be used for public advertisement and commercial promotion.

財團法人紡織產業綜合研究所
所長授權核發人: *sheng-fu chiu*
Authorized by president of Taiwan Textile Research Institute

Director, Department of Testing and Certification
紡織所檢測及驗證部 新莊市土城區承天路六號
Department of Testing and Certification, Taiwan Textile Research Institute
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R. O. C.)
Tel : +886-2-22670321 ext. 7107, 7110
+886-2-22698229 , +886-2-22698230
Fax : +886-2-22675108 , +886-2-22689839